

SGG COOL-LITE® SKGrey 148 II



Keep Exploring the New Boundaries of the finest style and performance

- Y2004 No.1** Off-line curved temperable single-silver coated glass launched in China
- Y2008 No.1** Off-line curved temperable double-silver coated glass launched in China
- Today** Saint-Gobain launches its first temperable pure grey double-silver in China

SGG COOL-LITE® SKGrey 148 II features double-silver coating, which further boosts the control of glass over solar radiation, with more optimal shading coefficient (SC value) and thermal conductivity coefficient (U value). It is the preferred product for high-grade buildings that seek grey upscale looks and good energy-saving performance.



Grey upscale looks

Meeting modern architectural design requirements, seeking unworldly architectural taste, and realizing perfect combination of classical and modern styles.



Excellent solar control performance

Superior shading performance, effectively reflecting 72% of solar heat, especially ideal application in areas where it is very hot in summer.



Excellent thermal insulation property

Good thermal insulation, keeping rooms warm in winter.



Eco-friendliness

Reducing energy consumption by 30%, effectively cutting the cost of air conditioning, and lowering energy consumption.



Energy-efficient application

The products are widely used in areas where there are relatively higher requirements for energy efficiency of buildings, surpassing China's energy-efficient design standard for windows and glass facade.



Product Parameters:

Type of coating	Color	Product Composition	Visible light (%)		SC		U value (W/m ² ·K)	
			Transmittance	Rout	EN	NFRC	Air	Argon
SKGrey 148 II	Grey	6-12-6	44	14	0.32	0.30	1.6	1.2

(*Average values according to EN673 standards and EN410 standards are subject to modification.)

CONTACT US

Shanghai Office

7th Floor, Office Tower,
Bund Center 222 Yan An Road (East)

TEL: 021 63611063
Fax: 021 63603779
P.C.: 200002

Nanjing Office

21 Xishanqiao South Road,
Zhong Hua Men Wai, Nanjing

TEL: 025 68574326
Fax: 025 52815301
P.C.: 210041

QingDao Office

254 Qianshan North Road,
Huangdao District, Qingdao

TEL: 0532 86907788
Fax: 0532 86907887
P.C.: 266500

Beijing Office

Rm. 1501, International Building,
19 Jianguomenwai Avenue, Beijing

TEL: 010 65941462
Fax: 010 65941465
P.C.: 100004

* Saint-Gobain reserves the right of final interpretation.